



Excel Plastics

Material Properties for Excel Colour PVC foam sheet.

The values are a list of typical results by testing large numbers of specimens under specified conditions.

Additional processing can influence the properties so we recommend caution must be adhered to when applied to the finished products.

PHYSICAL CHARACTERISTICS

Characteristic	Excel foam PVC sheet values
Base Polymer	Polyvinyl chloride PVC
Form	Semi – Finished sheet product
Thickness	3mm – 19mm
Smell	Odourless
Water absorption	0.10%
Water Solubility	Insoluble
Tensile strength at yield	13MPa
Modulus of Elasticity	0.9MPa
Flexural Strength	32MPa
Elongation at break	13%
Impact Resistance (CHARPY)	15kj/m ²
Impact Resistance (IZOD)	9MPa
Shore Hardness	30-40

THERMAL PROPERTIES

Property	Excel PVC foam sheet values
Vicat Softening temperature	73°C
Heat Deflection Temperature	
@1.8MPa	58°C
Coefficient of Linear expansion	4.47 X 10 ⁻⁵
Thermal Expansion	0.06W/mK
Service Temperature	-20°C to +60°C

ELECTRICAL PROPERTIES

Property	Excel foam PVC sheet values
Surface Resistivity (ohms)	10 ¹⁴ Ω
Volume Resistivity	10 ¹⁵ Ωcm
Dielectric Constant at 1MHZ	
dielectric strength	1.56



EXCEL FOAM SHEET AVAILABILITY

SHEET SIZES & TOLERANCES

Dimension	Excel foam PVC sheet sizes
Standard sheet sizes	2440mm x 1220mm
	3050mm x 1220mm
	3050mm x 1560mm
	3050mm x 2050mm
Other sizes are available to order	
Subject to minimum quantities.	

TOLERANCES

Length	-0 +10mm
Width	-0 +3mm
Thicknesses	+ /- 5%

Excel Plastics has no control over the use of the material by different end users. It does not guarantee the same results each time. The end user should make their own tests to determine the suitability of the product for the application. Excel Plastics cannot be held responsible for any incorrect handling of the product.